

TECHNICAL NOTE NUMBER 218

UNITED STATES DEPARTMENT OF AGRICULTURE

FOREST SERVICE

FOREST PRODUCTS LABORATORY

MADISON 5, WISCONSIN

REVISED

December 1953

WEIGHTS OF VARIOUS WOODS GROWN IN THE UNITED STATES

Calculated values of weights are necessarily approximate values owing to variations in moisture content, density, sapwood thickness, and the like that occur in different parts of the same timber. The calculated average weights obtained by the methods given here are not 100 percent accurate but are more accurate than the weight tables commonly given in grading rules as a basis for estimating timber transportation costs or other exacting transactions. The methods are also useful in roughly determining truck capacity needed to haul a given lot of timbers or the possibility of driving or towing logs.

There is enough difference between the weights of sawed and round timbers to require separate methods for estimating their average weights.

PART I. SAWED TIMBERS

Table 1 gives for various woods grown in the United States the average weights per cubic foot of sawed timbers at moisture content values of 8 and 15 percent, and the average weight of 1,000 board-feet when air-dry (15 percent moisture content). Factors for adjusting values for each 1 percent change in moisture content are given.

Table 1 is based on the weights and volumes of 2- by 2-inch, clear specimens from the top 4 feet of 16-foot butt logs of typical trees.

In any lot of lumber of a given species in the air-dry condition at 15 percent moisture content, the weight per cubic foot will rarely vary more than 10 percent from the figure given in table 1. The greatest changes in weight are those that occur in the early stages of drying of green wood. Changes in the moisture content of air-dry wood are attended by only

relatively small changes in weight per cubic foot, owing to the counter effect of change in volume as a result of accompanying shrinkage and swelling.

The values given in table 1 for weight per 1,000 board-feet at 15 percent moisture content were determined by multiplying the values per cubic foot at 15 percent by 83.3. The weights per 1,000 feet given in column 5 apply to theoretical board-foot measure (1,000 linear feet actually 1 inch thick and 12 inches wide, or equivalent) and not to a 1,000 board-foot lumber scale. Rough lumber is sometimes oversized and dressed lumber usually undersized with respect to nominal sizes. The values given in column 5 of table 1 will generally, therefore, need to be adjusted for actual shipments of lumber. The adjustment for 1- by 8-inch boards dressed to 25/32 inch in thickness and 7-1/2 inches in width is as follows:

$$\frac{25/32 \times 7-1/2}{1 \times 8} = 0.7324.$$

The value given in column 5 of table 1 (actual board-feet 15 percent moisture content) multiplied by this adjustment factor, gives the weight of the dressed lumber. The adjustment for rough oversized lumber is made in similar fashion, that is, actual size divided by nominal size. In like manner constants for any dressed size may be worked out and the weight per 1,000 board-feet computed.

Column (6) is an example of the weight per 1,000 board-feet of 1- by 8-inch boards dressed to 25/32 inch in thickness and 7-1/2 inches in width for various species. It has been computed by multiplying the values in column 5 by the foregoing constant 0.7324.

PART II. ROUND TIMBERS

The weight per unit volume of green round timbers, such as logs, pulpwood, posts, poles, and piling, may be estimated by means of tables 2, 3, and 4. Table 2 gives the average specific gravity and moisture content of sapwood and heartwood of various species in the green condition. Table 3 gives the percentage of sapwood in round timbers for various thicknesses, and diameters. Table 4 gives the weight per cubic foot of green wood at various specific gravities and moisture content values.

All three tables are necessary for estimating the weight per cubic foot of round timbers because in round timbers the proportions of sapwood and heartwood in the total volume often differ widely. Furthermore, the sapwood generally contains more water than the heartwood and both the sapwood and heartwood contain more moisture in the butt logs than in the top logs.

The following example illustrates how to determine the approximate weight per cubic foot of green round timber using tables 2, 3, and 4:

Example:

Given a species, say, black tupelo. The average specific gravity for the species is found from table 2 to be 0.46. The moisture content of the sapwood can be determined by actual measurement or estimated from table 2 as 115 percent. The moisture content of the heartwood can be determined by actual measurement or estimated from table 2 as 87 percent.

Next measure the average diameter of the timber and average width of sapwood. If the average diameter is, say, 10 inches and average sapwood thickness is 1-3/4 inches, then from table 3 the percentage of the volume of the round timber occupied by the sapwood is found to be 58 percent. The percentage of the volume occupied by the heartwood will therefore be, 100 percent minus 58 percent, or 42 percent.

Turning to table 4, and looking under a specific gravity of 0.46 for a sapwood moisture content of 115 percent, the weight per cubic foot is found to be 61.7 pounds per cubic foot. Under the same specific gravity value and a moisture content of 87 percent the weight of the heartwood is estimated to be half way between that given for moisture content values of 86 percent and 88 percent, or 53.7 pounds per cubic foot. (Moisture content values in the left column may be applied to either sapwood or heartwood.)

To find the weight in pounds per cubic foot of the round timber it is necessary to multiply the weight of sapwood by the percentage of sapwood divided by 100. Similarly for heartwood. Their sum gives the weight of the round timber in pounds per cubic foot.

Thus; $61.7 \times 58/100 = 35.8$ pounds

$53.7 \times 42/100 = 22.6$ pounds

Total weight of round timber per cubic foot = $35.8 + 22.6 = 58.4$ pounds.

Table 1.--Weights of sawed wood of various trees grown in the United States, under different conditions of moisture, and accompanying adjusting factors

Species	Weight in pounds per cubic foot		Weight per 1,000 board-feet air-dry		Species	Weight in pounds per cubic foot		Weight per 1,000 board-feet air-dry						
	Based on: Factorial (15 percent moisture and vol.-and vol.-ing values: same at a time as for each moisture: 1 percent change in board: (1 by 8 : of 15 : of 8 : moisture : percent : content : to 25/32 : by : 7-1/2)	Actual: Dressed: content: change in board: (1 by 8 : of 15 : of 8 : moisture : percent : content : to 25/32 : by : 7-1/2)	Based on: Factorial (15 percent moisture and vol.-and vol.-ing values: same at a time as for each moisture: 1 percent change in board: (1 by 8 : of 15 : of 8 : moisture : percent : content : to 25/32 : by : 7-1/2)	Actual: Dressed: content: change in board: (1 by 8 : of 15 : of 8 : moisture : percent : content : to 25/32 : by : 7-1/2)		Based on: Factorial (15 percent moisture and vol.-and vol.-ing values: same at a time as for each moisture: 1 percent change in board: (1 by 8 : of 15 : of 8 : moisture : percent : content : to 25/32 : by : 7-1/2)	Actual: Dressed: content: change in board: (1 by 8 : of 15 : of 8 : moisture : percent : content : to 25/32 : by : 7-1/2)							
HARDWOODS														
Alder, red	28.8	0.112	2,400	1,760	Magnolia, southern	34.4	0.162	2,960	2,170	Douglas-fir	34.3	0.170	2,860	2,090
Apple	48.5	.133	4,040	2,960	Manzanita	70.0	.241	5,830	4,270	Coast type	31.8	.137	2,650	1,940
Ash	55.3	.142	2,940	2,150	Maple	34.2	.145	2,850	2,090	Rocky Moun-	30.5	.179	2,540	1,860
Blue	40.7	.208	3,390	2,480	Bigleaf	39.8	.150	3,410	2,500	tain type	22.5	.167	1,870	1,370
Green	40.7	.179	3,390	2,480	Black	37.0	.154	3,080	2,070	Alpine	26.4	.071	2,240	1,640
White	42.7	.175	3,560	2,610	Silver	33.9	.154	3,710	2,720	Balsam	28.3	.158	2,360	1,730
Aspen	42.7	.175	3,560	2,610	Sugar	44.5	.158	4,070	2,980	California	28.3	.145	2,360	1,730
Birch	27.3	.104	2,270	1,660	Mountain	47.7	.158	4,070	2,980	red	27.1	.129	2,260	1,660
Quaking	27.0	.129	2,250	1,650	Laurel	48.8	.158	4,070	2,980	Grand	28.3	.117	2,340	1,710
Basswood	26.0	.075	2,170	1,590	Oak	44.0	.150	3,670	2,690	Noble	29.0	.129	2,420	1,770
Beech	44.3	.162	3,690	2,700	Red	43.0	.150	3,670	2,690	Pacific	29.6	.129	2,420	1,770
American	38.8	.117	3,230	2,370	Cherry	45.8	.162	3,930	2,880	Whites	29.0	.150	2,440	1,810
paper	38.2	.095	3,240	2,370	Laurel	47.2	.162	3,930	2,880	Hemlock	29.6	.129	2,420	1,770
Sweet	47.2	.175	3,930	2,880	Northern	45.5	.162	3,930	2,880	Juniper	36.7	.179	3,060	2,240
Yellow	43.4	.142	3,620	2,650	Southern	43.8	.162	3,650	2,670	Larch	39.4	.170	3,280	2,400
Buckeye	25.5	.104	2,120	1,550	Water	41.1	.142	3,420	2,500	alligator	25.4	.167	2,120	1,550
California	27.4	.145	2,280	1,670	Willow	44.6	.142	3,720	2,720	Pines	29.2	.152	2,520	1,820
laural	39.5	.183	3,290	2,410	White	45.0	.162	3,750	2,750	Eastern	28.2	.142	2,450	1,780
Cherry, black	36.1	.183	3,010	2,200	Swamp	47.9	.162	3,990	2,920	Jack	28.2	.150	2,590	1,900
Chestnut	30.5	.145	2,540	1,860	Chestnut	48.5	.167	4,040	2,960	Lodgepole	35.8	.162	3,060	2,240
Chinquapin	32.3	.145	2,690	1,970	White-orange	46.8	.167	3,900	2,860	Pitch	27.5	.162	2,380	1,740
Cottonwood	24.5	.104	2,040	1,490	Flametto	57.5	.167	4,770	3,490	Red	30.4	.142	2,620	1,920
Eastern	28.9	.142	2,410	1,770	cabage	29.6	.087	2,470	1,810	Southern	27.1	.129	2,330	1,710
Cucumber tree	33.3	.142	2,860	2,090	Persimmon	50.8	.158	4,230	3,100	Yellow	27.4	.175	2,380	1,740
Dogwood	51.5	.120	4,290	3,140	common	23.2	.100	1,950	1,410	Longleaf	25.8	.142	2,010	1,470
Pacific	45.9	.142	3,820	2,800	Poplar	36.5	.167	3,040	2,230	Shortleaf	27.2	.175	2,370	1,740
American	36.3	.117	3,020	2,210	Balsam	35.5	.153	3,030	2,220	Sugar	28.1	.145	2,340	1,710
Cedar	45.9	.187	3,820	2,800	Sweet gum	36.4	.153	3,030	2,220	Western	29.4	.187	2,450	1,790
Rock	44.6	.208	3,680	2,700	Sycamore	35.7	.153	2,970	2,180	White	28.7	.187	2,450	1,790
Slippery	37.8	.154	3,150	2,310	American	34.7	.153	2,970	2,180	Tamarack	37.6	.250	3,130	2,290
Hackberry	37.4	.175	3,120	2,290	Atlantic	30.3	.150	2,520	1,850	Tew, Pacific	45.7	.250	3,810	2,790
Hickory	51.4	.145	4,280	3,130	Redwood (old-growth)	35.4	.150	3,050	2,220					
Mockernut	46.5	.212	4,570	3,260	Redwood (new-growth)	35.5	.150	3,050	2,220					
Pignut	53.4	.229	4,270	3,130	White	31.4	.157	2,720	1,990					
Shagbark	51.2	.129	4,080	2,950	Eastern	30.4	.170	2,630	1,930					
Shellbark	49.0	.170	3,720	2,720	Western	23.0	.129	1,980	1,450					
Water	44.6	.229	3,720	2,720	White-orange	32.6	.170	2,630	1,930					
Holly	39.8	.133	3,320	2,430	Redcedar	31.6	.170	2,630	1,930					
Honeylocust	45.3	.250	3,770	2,760	Eastern	23.0	.129	1,980	1,450					
Rophrornbeam	50.0	.167	4,170	3,050	Western	32.2	.187	2,790	2,040					
Locust, black	49.0	.224	4,080	2,950	Incense	25.5	.183	2,120	1,550					
Madrone	44.6	.150	3,800	2,780	Northern	21.8	.145	1,820	1,330					
Pacific	45.6	.150	3,800	2,780	Port-Orford	30.1	.175	2,510	1,840					
					Western	23.4	.137	1,950	1,430					

To adjust value to any desired moisture content, add factor to value to be adjusted for each 1 percent increase in moisture content; subtract factor from value to be adjusted for each 1 percent decrease in moisture content. These factors take shrinkage well with moisture changes into consideration.

Table 2.--Average moisture content and specific gravity of green wood

Species	Moisture content ¹		Average specific gravity ²	Species	Moisture content ¹		Average specific gravity ²
	Heartwood	Sapwood			Heartwood	Sapwood	
SOFTWOODS							
Baldcypress	121	171	0.42	Basswood, American	81	133	0.32
Cedar				Beech, American	55	72	.56
Alaska	32	166	.42	Birch	89	72	.48
Atlantic white			.31	Paper	75	70	.60
Eastern redcedar	33	35	.44	Sweet	74	72	.55
Incense	40	213	.35	Yellow			.32
Northern white			.29	Buckeye, yellow			.51
Port-Oxford	50	98	.40	Bitternut			.47
Western redcedar	50	249	.31	California-laurel	58	65	.40
Douglas-fir			.45	Cherry, black	120		.42
Coast type	37	115	.41	Chestnut, American			.32
Intermediate type	34	154	.40	Chinkapin, golden	162	146	.64
Rocky Mountain type	30	112	.40	Cottonwood, black			.64
Fir				Dogwood, flowering			.62
Alpine			.31	Elm			.46
Balsam			.34	American	95	92	.59
California red			.37	Cedar	66	61	.57
Grand	91	156	.37	Rock	44	57	.49
Noble	34	115	.35	Hackberry	61	65	.60
Pacific silver	55	164	.35	Bitternut	80	54	.64
White	98	160	.35	Noekernut	70	52	.66
Hemlock			.38	Pignut	71	49	.61
Eastern	97	119	.38	Red	69	52	.61
Western	85	170	.38	Sand	68	50	.50
Larch, western	54	119	.51	Water	97	62	.63
Fine				Holly, American			.66
Eastern white			.34	Hophornbeam, eastern			.58
Lodgepole	41	120	.38	Locust, black			.44
Ponderosa	40	143	.38	Madrone, Pacific			.56
Red	32	134	.41	Magnolia	80	104	.56
Southern yellow			.47	Maple			.51
Loblolly	33	110	.46	Silver (soft)	58	97	.81
Longleaf	31	106	.46	Sugar (hard)	65	72	.56
Shortleaf	32	122	.35	Oak	76	75	.51
Sugar	20	219	.36	Live			.56
Western white	62	148	.38	Northern red	80	69	.52
Redwood (old-growth)	86	210	.38	Southern red	83	73	.52
Spruce				Tan			.56
Eastern	34	128	.32	Water	81	81	.60
Engelmann	51	173	.37	White	64	78	.56
Sitka	41	142	.49	Willow	82	74	.76
Tamarack	49			Orange-orange			.64
				Perisperm, common			.46
HARDWOODS				Sweetgum	79	137	.46
Alaer, red			.37	Sycamore, American	114	130	.46
Apple	81	74	.61	Tupelo			.46
Ash			.45	Black	87	115	.46
Black	95		.55	Swamp	101	108	.46
Green	46		.55	Water	150	116	.51
White	44		.55	Walnut, black	90	73	.54
Aspen	95	113		Willow, black			.40
				Yellow-poplar	83	106	.40

¹Based on weight when oven-dry.

²Based on weight when oven-dry and volume when green.

Table 3.--Sapwood, in percent of volume, of round timbers

Sapwood thickness: Inches	Average diameter of timber in inches															
	4	5	6	7	8	9	10	11	12	13	14	15	16			
1/4	23	19	16	14	12	11	10	9	8	7	6					
1/2	44	36	31	27	23	21	19	17	16	14	12	11	10	9	8	
3/4	61	51	44	38	34	31	28	25	23	20	18	16	14	13	12	
1	75	64	56	49	44	40	36	33	31	27	23	20	18	16	15	
1-1/4	86	75	66	59	53	48	44	40	37	33	29	25	21	18	16	
1-1/2	94	84	75	67	61	56	51	47	44	38	34	31	27	23	20	
1-3/4	98	91	83	75	68	63	58	54	50	44	39	36	31	27	23	
2	100	96	89	82	75	69	64	60	56	49	44	41	36	31	27	
2-1/4	...	99	94	87	81	75	70	65	61	54	48	46	41	36	31	
2-1/2	...	100	97	92	86	80	75	70	66	59	53	51	46	41	36	
2-3/4	99	95	90	85	80	75	71	63	57	56	51	46	41	
3	100	98	94	89	84	79	75	67	61	60	56	51	46	
3-1/4	99	96	92	88	83	79	71	65	64	60	56	51	
3-1/2	100	98	95	91	87	83	75	68	68	64	60	56	
3-3/4	100	100	94	90	86	78	72	75	72	68	64	
4	100	99	96	93	89	82	75	78	75	72	68	
4-1/4	100	98	95	91	85	78	81	78	75	72	
4-1/2	100	99	97	94	87	81	84	81	78	75	
4-3/4	100	98	96	90	84	87	84	81	78	
5	100	99	97	92	86	89	87	84	81	

Table 4.--Weight in pounds per cubic foot of green wood at various specific

Moisture content: Percent	Specific gravity, based on oven-dry weight and green volume																				
	0.30	0.32	0.34	0.36	0.38	0.40	0.42	0.44	0.46	0.48	0.50	0.52	0.54	0.56	0.58	0.60	0.62	0.64	0.66	0.68	0.70
30	24.3	26.0	27.6	29.2	30.8	32.4	34.1	35.7	37.3	38.9	40.6	42.2	43.8	45.4	47.0	48.7	50.3	51.9	53.5	55.2	56.8
32	24.7	26.4	28.0	29.7	31.3	32.9	34.6	36.2	37.9	39.5	41.2	42.8	44.5	46.1	47.8	49.4	51.1	52.7	54.4	56.0	57.7
34	25.1	26.8	28.4	30.1	31.8	33.4	35.1	36.8	38.5	40.1	41.8	43.5	45.2	46.8	48.5	50.2	51.8	53.5	55.2	56.9	58.5
36	25.5	27.2	28.9	30.6	32.2	33.9	35.6	37.3	39.0	40.7	42.4	44.1	45.8	47.5	49.2	50.9	52.6	54.3	56.0	57.7	59.4
38	25.8	27.6	29.3	31.0	32.7	34.4	36.2	37.9	39.6	41.3	43.1	44.8	46.5	48.2	49.9	51.7	53.4	55.1	56.8	58.6	60.3
40	26.2	28.0	29.7	31.4	33.2	34.9	36.7	38.4	40.2	41.9	43.7	45.4	47.2	48.9	50.7	52.4	54.2	55.9	57.7	59.4	61.2
42	26.6	28.4	30.1	31.9	33.7	35.4	37.2	39.0	40.8	42.5	44.3	46.1	47.8	49.6	51.4	53.2	54.9	56.7	58.5	60.3	62.0
44	27.0	28.8	30.6	32.3	34.1	35.9	37.7	39.5	41.3	43.1	44.9	46.7	48.5	50.3	52.1	53.9	55.7	57.5	59.3	61.1	62.9
46	27.3	29.2	31.0	32.8	34.6	36.4	38.3	40.1	41.9	43.7	45.6	47.4	49.2	51.0	52.8	54.7	56.5	58.3	60.1	62.0	63.8
48	27.7	29.6	31.4	33.2	35.1	36.9	38.8	40.6	42.5	44.3	46.2	48.0	49.9	51.7	53.6	55.4	57.3	59.1	61.0	62.8	64.6
50	28.1	30.0	31.8	33.7	35.6	37.4	39.3	41.2	43.1	44.9	46.8	48.7	50.5	52.4	54.3	56.2	58.0	59.9	61.8	63.6	65.5
52	28.5	30.4	32.2	34.1	36.0	37.9	39.8	41.7	43.6	45.5	47.4	49.3	51.2	53.1	55.0	56.9	58.8	60.7	62.6	64.5	66.4
54	28.8	30.8	32.7	34.6	36.5	38.4	40.4	42.3	44.2	46.1	48.0	50.0	51.9	53.8	55.7	57.7	59.6	61.5	63.4	65.3	67.3
56	29.2	31.2	33.1	35.0	37.0	38.9	40.9	42.8	44.8	46.7	48.7	50.6	52.6	54.5	56.5	58.4	60.4	62.3	64.2	66.2	68.1
58	29.6	31.5	33.5	35.5	37.5	39.4	41.4	43.4	45.4	47.3	49.3	51.3	53.2	55.2	57.2	59.2	61.1	63.1	65.1	67.0	69.0
60	30.0	31.9	33.9	35.9	37.9	39.9	41.9	43.9	45.9	47.9	49.9	51.9	53.9	55.9	57.9	59.9	61.9	63.9	65.9	67.9	69.9
62	30.5	32.3	34.4	36.4	38.4	40.4	42.5	44.5	46.5	48.5	50.5	52.6	54.6	56.6	58.6	60.7	62.7	64.7	66.7	68.7	70.8
64	30.7	32.7	34.8	36.8	38.9	40.9	43.0	45.0	47.1	49.1	51.2	53.2	55.3	57.3	59.4	61.4	63.4	65.5	67.5	69.6	71.6
66	31.1	33.1	35.2	37.3	39.4	41.4	43.5	45.6	47.6	49.7	51.8	53.9	55.9	58.0	60.1	62.2	64.2	66.3	68.4	70.4	72.5
68	31.4	33.5	35.6	37.7	39.8	41.9	44.0	46.1	48.2	50.3	52.4	54.5	56.6	58.7	60.8	62.9	65.0	67.1	69.2	71.3	73.4
70	31.8	33.9	36.1	38.2	40.3	42.4	44.6	46.7	48.8	50.9	53.0	55.2	57.3	59.4	61.5	63.6	65.8	67.9	70.0	72.1	74.3
72	32.2	34.3	36.5	38.6	40.8	42.9	45.1	47.2	49.4	51.5	53.7	55.8	58.0	60.1	62.3	64.4	66.5	68.7	70.8	73.0	75.1
74	32.6	34.7	36.9	39.1	41.3	43.4	45.6	47.8	49.9	52.1	54.3	56.5	58.6	60.8	63.0	65.1	67.3	69.5	71.7	73.8	76.0
76	32.9	35.1	37.3	39.5	41.7	43.9	46.1	48.3	50.5	52.7	54.9	57.1	59.3	61.5	63.7	65.9	68.1	70.3	72.5	74.7	76.9
78	33.3	35.5	37.8	40.0	42.2	44.4	46.7	48.9	51.1	53.3	55.5	57.8	60.0	62.2	64.4	66.6	68.9	71.1	73.3	75.5	77.8
80	33.7	35.9	38.2	40.4	42.7	44.9	47.2	49.4	51.7	53.9	56.2	58.4	60.7	62.9	65.1	67.4	69.6	71.9	74.1	76.4	78.6
82	34.1	36.3	38.6	40.9	43.2	45.4	47.7	50.0	52.2	54.5	56.8	59.1	61.3	63.6	65.9	68.1	70.4	72.7	75.0	77.2	79.5
84	34.4	36.7	39.0	41.3	43.6	45.9	48.2	50.5	52.8	55.1	57.4	59.7	62.0	64.3	66.6	68.9	71.2	73.5	75.8	78.1	80.4
86	34.8	37.1	39.5	41.8	44.1	46.4	48.7	51.1	53.4	55.7	58.0	60.4	62.7	65.0	67.3	69.6	72.0	74.3	76.6	78.9	81.2
88	35.2	37.5	39.9	42.2	44.6	46.9	49.3	51.6	54.0	56.3	58.7	61.0	63.3	65.7	68.0	70.4	72.7	75.1	77.4	79.8	82.1
90	35.6	37.9	40.3	42.7	45.1	47.4	49.8	52.2	54.5	56.9	59.3	61.7	64.0	66.4	68.8	71.1	73.5	75.9	78.2	80.6	83.0
92	35.9	38.3	40.7	43.1	45.5	47.9	50.3	52.7	55.1	57.5	59.9	62.3	64.7	67.1	69.5	71.9	74.3	76.7	79.1	81.5	83.9
94	36.3	38.7	41.2	43.6	46.0	48.4	50.8	53.3	55.7	58.1	60.5	62.9	65.4	67.8	70.2	72.6	75.1	77.5	79.9	82.3	84.7
96	36.7	39.1	41.6	44.0	46.5	48.9	51.4	53.8	56.3	58.7	61.2	63.6	66.0	68.5	70.9	73.4	75.8	78.3	80.7	83.2	85.6
98	37.1	39.5	42.0	44.5	46.9	49.4	51.9	54.4	56.8	59.3	61.8	64.2	66.7	69.2	71.7	74.1	76.6	79.1	81.5	84.0	86.5
100	37.4	39.9	42.4	44.9	47.4	49.9	52.4	54.9	57.4	59.9	62.4	64.9	67.4	69.9	72.4	74.9	77.4	79.9	82.4	84.9	87.4
105	38.4	40.9	43.5	46.1	48.6	51.2	53.7	56.3	58.8	61.4	64.0	66.5	69.1	71.6	74.2	76.8	79.3	81.9	84.4	87.0	89.5
110	39.3	41.9	44.6	47.2	49.8	52.4	55.0	57.7	60.3	62.9	65.5	68.1	70.8	73.4	76.0	78.6	81.2	83.9	86.5	89.1	91.7
115	40.2	42.9	45.6	48.3	51.0	53.7	56.3	59.0	61.7	64.4	67.1	69.8	72.4	75.1	77.8	80.5	83.2	85.9	88.5	91.2	93.9
120	41.2	43.9	46.7	49.4	52.2	54.9	57.7	60.4	63.1	65.9	68.6	71.4	74.1	76.9	79.6	82.4	85.1	87.9	90.6	93.4	96.1
125	42.1	44.9	47.7	50.5	53.4	56.2	59.0	61.8	64.6	67.4	70.2	73.0	75.8	78.6	81.4	84.2	87.0	89.9	92.7	95.5	98.3
130	43.1	45.9	48.8	51.7	54.5	57.4	60.3	63.1	66.0	68.9	71.8	74.6	77.5	80.4	83.2	86.1	89.0	91.9	94.7	97.6	100.5
135	44.0	46.9	49.9	52.8	55.7	58.7	61.6	64.5	67.5	70.4	73.3	76.3	79.2	82.1	85.1	88.0	90.9	93.8	96.8	99.7	102.6
140	44.9	47.9	50.9	53.9	56.9	59.9	62.9	65.9	68.9	71.9	74.9	77.9	80.9	83.9	86.9	89.9	92.9	95.8	98.8	101.8	104.8
145	45.9	48.9	52.0	55.0	58.1	61.2	64.2	67.3	70.3	73.4	76.4	79.5	82.6	85.6	88.7	91.7	94.8	97.8	100.9	104.0	107.0
150	46.8	49.9	53.0	56.2	59.3	62.4	65.5	68.6	71.8	74.9	78.0	81.1	84.2	87.4	90.5	93.6	96.7	99.8	103.0	106.1	109.2